

Certificate of Analysis

John Desmond Ltd
Architectural & Specialist Metalwork Contractors
58 Weir Road
Wimbledon
London
SW19 8UG

Sample Details: Powder Coated Metal with Dexo Antimicrobial Additive
Date Tested: 30th November 2015
Method: Determination of Antibacterial Activity using Modified ISO22196:2007(E)
Challenge Organism: *Staphylococcus epidermidis* RP62A (ATCC 35984)
Temperature: 25°C

Sample	Contact Time		Reduction from Initial	
	0 Hours	24 Hours	Log10	%
Dexo Powder Coating	3.8x10 ⁵	<1.0x10 ³	>2.58	>97.4

The above data shows the change in population following contact with the surface of the sample listed for 24 hours at 25° degrees under a RH >95%



Professor Anthony C. Hilton
Head of Biological & Biomedical Sciences